BASE PAPER FOR DECORATIVE FACING MATERIALS, BOfon

аснова
завод газетной бумаги

APPLYING

is used in the production of decorative film for wood-based panel materials (chipboard, MDF)

ТУ BY 790282162.011-2015

Values	BOfon
Paper grammage, g/m2	60,0±2,0; 65,0±2,0; 70,0±3,0; 75,0±2,0; 80,0±2,0; 90,0±3,0; 100,0±3,0; 110,0±3,0
Bursting force , N, at least: - for dry paper: 110 g/m² 100 g/m² 90 g/m² 75-80 g/m² 65-70 g/m² 60 g/m² - for wet paper	 35 33 32 29 28 26 6,5
Ash content, %	18-42
air permeabilty, s/100sm3	18-25
Soreness – the number of sores per 1 m2: from 0,3 to 1 mm²	5
pH extract	6,5-7,2
Smoothness by Beck, s	30-80
Permeability of paper, s	6
Paper color	according to an agreed standard sample in a pressed form