OFFSET PAPER

аснова
завод газетной бумаги

APPLYING

is used in the manufacture of illustrative and textual publications by offset and other methods, as well as the production of school and general notebooks, paper for plotters and other paper and white products

Values	№1
Paper grammage, g/m2	50,0±2,0; 55,0±2,0; 60,0±2,0; 65,0±2,0; 70,0±2,0; 80,0±2,5; 90,0±2,5; 100,0±3,0; 120,0±4,0
Density, g/sm³	0,65-0,95
Fracture strength with multiple bends in the transverse direction, the number of double bends: from 50 to 70 g/m2 from 80 to 120 g/m2	 ≥7 ≥10
Smoothness, s, at least	25
Whiteness, %, at least	79
Soreness – the number of sores per 1 m2	100
Moisture content, %	5,5±1,0
Coobb, g/m2	18-30
Ash content, %	at least 8
Gluing degree, mm	1,0
Breaking length of paper, m	at least 4,0
Opacity, %, not less than: from 50 to 70 g/m2 from 80 to 120 g/m2	 82 85

On the surface of the paper, folds, wrinkles, polished stripes, transparent spots and holes visible to the naked eye are not allowed.

Inconspicuous folds, wrinkles, polished stripes, transparent spots and holes are allowed, which cannot be detected during the manufacturing process, if the rate of these intra-roll defects does not exceed 5.0%