BLEACHED BAG PACKAGING PAPER

аснова
завод газетной бумаги

APPLYING

is intended for the production of paper bags, as well as for food packaging, packaging for packaging industrial products

ТУ BY 790282162.014-2017

Values	"БУП"
Paper grammage, g/m2	40,0±2,0; 50,0±2,0; 60,0±2,0; 70,0±2,0; 80,0±2,0; 90,0±2,0; 100,0±3,0; 110,0±3,0
Coobb, g/m2	30
Force (MD/CD), N 40 g/m² 50 g/m² 60-70 g/m² 80-90 g/m² 100-110 g/m²	 ≥50/15 ≥55/15 ≥60/20 ≥70/30 ≥90/40
Stretch (MD/CD), %, at least	1,1/3,0
Tear strenght (MD/CD), mN 40 г/м² 50 г/м² 60 г/м² 70 г/м² 80 г/м² 90 г/м² 100 г/м² 110г/м²	 ≥260/300 ≥350/350 ≥400/450 ≥450/600 ≥500/650 ≥600/700 ≥700/750 ≥750/850
Whiteness, %, at least	80

On the surface of the paper, folds, wrinkles, polished stripes, transparent spots and holes visible to the naked eye are not allowed.

Subtle folds, wrinkles, polished stripes, transparent spots and holes are allowed, which cannot be detected during the manufacturing process, if the rate of these intra-roll defects does not exceed 3.0%.