TINTED NEWSPRINT PAPER

аснова
завод газетной бумаги

APPLYING

is intended for printing on high-speed newspaper aggregates of newspapers, book-magazine and other paper products with black-and-white and color illustrations

Values			
Paper grammage, g/m2	45,0±1,0	45,0±1,5	48,8±1,5
Density, g/sm³	0,60-0,61	0,60-0,61	0,60-0,61
Breaking length of paper, m	3500-3900	3800-4200	3100-4400
Moisture content, %	7,5-8,5	7,5-8,5	7,5-8,5
Smoothness, s	45-50	45-50	45-50
Opacity of paper, %	96-99	96-99	96-99
Paper color	according to an agreed standard-sample		
Soreness – the number of sores per 1 m2: – from 0,5 to 1,5 mm²; – over 1,5 mm²	≤40 0	≤50 0	≤50 0

On the surface of the paper, folds, wrinkles, polished stripes, transparent spots and holes visible to the naked eye are not allowed.

Subtle folds, wrinkles, polished stripes, transparent spots and holes are allowed, which cannot be detected during the manufacturing process, if the rate of these intra-roll defects does not exceed 2.0%

According to the color parameters, the paper is marked with the name of the color that characterizes a certain shade.